

## Technical Data Sheet

# ACS Material Thermal Conductive Pad

Table of Contents

1-Features

2-Characterizations

3 - Application Fields

**Contact Information:** 

Manufacturer: ACS Material, LLC. Address: 959 E Walnut St. Suite 100 Pasadena, CA 91106, USA Phone: (866)-227-0656 Fax: (781)-518-0284 E-Mail: contact@acsmaterial.com Revision: 062623 The soft thermal pad sealing material with a thermal conductivity range of 1.0~12.0W/m\*K is suitable for applications with low assembly stress. This material has self-adhesiveness and weak elasticity, can be compounded with different reinforcing materials to achieve good body strength, and can be well attached to material interfaces, resulting in low thermal resistance and good shock absorption. At the same time, the thermal pad adopts an organic silicon formulation system, which is non-toxic, odorless, non-corrosive, and complies with RoHS directives and related environmental requirements.



## 1. Features

- Good insulation and high/low temperature resistance.
- Flame retardant rating of UL94 V0
- Good workability and flexibility

### 2. Characterizations

Туре	А	В	Test Standard
Color	Grey/Optional	Grey/Optional	Visual inspection
Thermal Conductive	2.0 W/m*K	8.0 W/m*K	ISO22007-2
Size	200x400x2 mm	50x50x1 mm	-
Thickness	0.4~10 mm	0.4~10 mm	ASTM D374
Density	2.1 g/cc	3.4 g/cc	ASTM D792
Hardness	5~80 Shore00	20~80 Shore00	ASTM D2240
Flame Retardant Rating	V0	V0	UL94
Tensile Strength	0.1 MPa	0.1 MPa	ASTM D412
Elongation at Break	20%	30%	ASTM D412
Breakdown Voltage	>10 kV/mm	>6 kV/mm	ASTM D149
Volume Resistivity	>10 <sup>12</sup> Ohm*cm	>10 <sup>11</sup> Ohm*cm	ASTM D257
D4~D10 Content	<100 ppm	<100 ppm	GC
Recommended using temperature range	-40 ~ +150 °C	-40 ~ +150 °C	-



### **3.** Application Fields

Square battery/straight cold plate

**Disclaimer:** ACS Material, LLC believes that the information in this Technical Data Sheet is accurate and represents the best and most current information available to us. ACS Material makes no representations or warranties either express or implied, regarding the suitability of the material for any purpose or the accuracy of the information contained within this document. Accordingly, ACS Material will not be responsible for damages resulting from use of or reliance upon this information.

TDS