



Technical Data Sheet

ACS Material Monolayer WSe₂ on SiO₂ (20-50μm)

Table of Contents

[1 – Preparation Method](#)

[2 – Characterizations](#)

[3 – Application Fields](#)

Contact Information:

Manufacturer: ACS Material, LLC.

Address: 959 E Walnut St., Suite 100,

Pasadena, CA 91106, USA

Phone: (866)-227-0656

Fax: (781)-518-0284

E-Mail: contact@acsmaterial.com


Revision: 103017

1. Preparation Method

CVD Method

2. Characterizations

Substrate:	SiO ₂
Size:	9 mm*9 mm
Thickness:	0.6-0.8 nm
Diameter range:	20-50 μm



Typical Microscope Image of ACS Material Monolayer WSe₂ on SiO₂ (20-50μm)

3. Application Fields

An excellent device material for studying the number of layers and fluorescence effects.

Disclaimer: ACS Material, LLC believes that the information in this Technical Data Sheet is accurate and represents the best and most current information available to us. ACS Material makes no representations or warranties either express or implied, regarding the suitability of the material for any purpose or the accuracy of the information contained within this document. Accordingly, ACS Material will not be responsible for damages resulting from use of or reliance upon this information.